

Ezact™ Classic

Special Features:

- Made from natural latex rubber. Easy to don and comfortable to wear.
- No sensitization response conducted in conformance with ISO 13485 quality standard.
- Powdered with human absorbable corn starch.
- Safe grip finish with textured surface.
- Penetration of Phi-X174 Bacteriophage tested with ASTM F 1671.



Product Specification Ref. 1010

Product Description	Latex Surgical Gloves, pre-powdered, anatomic shape, beaded cuff, textured surface in the grip area, size embossed, sterile.					
Size		5.5 6.0	6.5 7.0 7.	.5 8.0	8.5 9.0	
Palm Width	mm	70±6 76±6	83±6 89±6 95	±6 102±6 10	08±6 114±6	
Overall Length	mm	290 ± 5				
	inch	11.42 ± 0.2				
Single Wall Thickness		Finger	Palm	Cuff	Cuff	
	mm	0.22 ± 0.03	0.22 ± 0.03	0.18 ± 0.03		
	mil	8.66 ± 1.18	8.66 ± 1.18	7.09 ± 1.1	8	
	Туре	Before Aging		After Aging		
		Standard	MocareHealth	Standard	MocareHealth	
					4.0	
	Force at break (N)	9	18	9	16	
Physical Property	Force at break (N) Tensile strength (Mpa)	9 24 (min)	18 29	9 18 (min)	16 24	
Physical Property						
	Tensile strength (Mpa)	24 (min)	29	18 (min)	24	
	Tensile strength (Mpa) Ultimate elongation (%) Stress at 500%	24 (min) 750	29 880	18 (min)	24	
Property	Tensile strength (Mpa) Ultimate elongation (%) Stress at 500% elongation (Mpa)	24 (min) 750 5.5 (max) 71, ASTM D 3577, A	29 880 2.5	18 (min) 560 -	24 820 -	

Mocare Health Co., Ltd.

Tel: 886-4-8762747 Website: http://www.mocarehealth.com Fax: 886-4-8762749 E-mail: service@mocarehealth.com

Office: No.216, Laonong Rd., Tianzhong Township, Changhua County, 52046, Taiwan (R.O.C.)











