# SurPure<sup>®</sup> Micro



### **Microsurgery Latex Surgical Gloves**

The specialty gloves with great sensitivity and grip performance. Designed for cardiology, neurosurgery, ophthalmology and ENT surgery departments to conduct microsurgeries.

- Colored brown to reduce glare from operating lights
- Purified with chlorination, gives a premium sense of touch and the reduced protein content for less skin allergies
- 20% thinner\* for the sensitive tactile touch (\*compared with model SurPure<sup>®</sup> Prime)
- Each glove passes more than 320 test items before delivery
- Made by using specially-designed hand mold and Mocare Health<sup>®</sup> unique formula
- Dipped with 2 layers of latex for minimizing the pre-existed pinholes
- Polymer coating, easy donning with damp or dry hands
- Exceed international quality standards
- Pass Penetration of Phi-X174 Bacteriophage test (ASTM F1671)
- In conformity with regulation EU 2016-425 PPE Module B

20000002	
Surgical Gloves	2 relati (CityES
Latex · Powder-Free	STITPUTE MILLIO
A separation for the second se	Latex - Powder-Free
Annumentation     Annumentation     Annumentation	A chulloni
Alter provides, fairs more, fairs and the lands	The state of the s
Control of the same has an unit and the same and the	Port (in party view)     (ii) a many of early
PT - Lassificação     Anno 2005, Seria contrator colos Minister     Anno 2005, Seria dos contratos Minister     Anno 2006 do rectanção	Saint 1
<ul> <li>4 4 40</li></ul>	III - Constanting and a second a secon
2 V Istorica CC 10	
Charace The Second Seco	The second secon
The Additional of the Addition	2 7 22
REF 1718 MocareHealth	



## SurPure<sup>®</sup> Micro Microsurgery Latex Surgical Gloves

- Curved fingers for ergonomic fit.
- Non-beaded cuff to better fit forearms.
- Optional pinhole AQL 0.65 1.5 with the quality insurance that each glove is air inflated and visually inspected.
- Gamma Irradiation for the improved certainty of sterility. No ethylene oxide (EtO) residues concern of being harmful to human body.
- Airtight packaging for easier storage, keep gloves in an ideal state before using, and no paper scraps when opening.

Size		5.5	6.0	6.5	7.0	7.5	8.0	8.5	9.0	
Palm Width	mm	70±6	76±6	83±6	9 89±6	95±6	102±6	108±6	114±6	
Overall	mm	305 ± 5								
Length	inch	12.01 ± 0.2								
		Finger			Palm			Cuff		
Single Wall Thickness	mm	0.17	75 ± 0.03		0.18	± 0.03		0.18 ± 0.03		
	mil	6.8	89± 1.18		7.09	± 1.18		7.09± 1	.18	

#### Specifications & reference :

	Туре	Befo	ore Aging	After Aging		
	Type	Standard	SurPure <sup>®</sup> Micro <sup>*</sup>	Standard	SurPure <sup>®</sup> Micro <sup>*</sup>	
Typical Physical	Force at break (N)	9	13 🗸	9	12 🗸	
Property	Tensile strength (Mpa)	24 (min)	27 🖌	18 (min)	25 🖌	
Performance	Ultimate elongation (%)	750	860 🗸	560	840 🗸	
	Stress at 500% elongation (Mpa)	5.5 (max)	2.6 🗸			

Remark\*: The figures of physical properties given in the form and the chart indicate an average result obtained through numerous test reports.

# wife-Layer Design Additional latex layer Polymer coating

### Colored brown to reduce glare from operating light

Mocare Health® has specialized in medical gloves manufacturing for over 40 years. We have gloves dipping machines of our own design and the complete manufacturing technique in medical gloves industry. It is our obligation to provide reassuring medical gloves for healthcare workers to best perform their expertise.

#### Mocare Health Co., Ltd.

- No. 216, Laonong Rd., Tianzhong Township, Changhua County 52046, Taiwan (R.O.C.)
- Tel: 886-4-8762747
- Fax: 886-4-8762749
- E-mail: service@mocarehealth.com
- www.mocarehealth.com

